

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-001345

(43)Date of publication of application : 06.01.1998

---

(51)Int.Cl. C04B 28/02  
// (C04B 28/02  
C04B 14:06  
C04B 24:26  
C04B 14:28 )  
C04B111:50

---

(21)Application number : 08-156615

(71)Applicant : MITSUBISHI MATERIALS CORP

(22)Date of filing : 18.06.1996

(72)Inventor : ANAZAWA MASAOKI  
TANAKA YOSHIO  
JITOUZONO HIROSHI

---

### (54) SINGLE POWDER TYPE POLYMER CEMENT COMPOSITION FOR HALF DEFLECTIVE PAVEMENT

#### (57)Abstract:

PROBLEM TO BE SOLVED: To lessen drying shrinkage and to improve a fluidity, crack resistance and strength developability by incorporating cement, fine limestone powder, silica sand, reemulsifiable powder resin and powder additive into the compsn.

SOLUTION: This compsn. is obtd. by uniformly compounding 5 to 100 pts.wt. fine limestone powder, fly ashes or blast furnace slag having a Blaine's value of 1000 to 600cm<sup>2</sup>/g, 3 to 200 pts.wt. silica sand or limestone aggregate having a grain size of 0.01 to 1.0mm and 2 to 46 pts.wt. reemulsifiable powder resin consisting of a vinyl acetate resin or powder asphalt having an average grain size of 20 to 60μm as well as 0.1 to 10 pts.wt. water reducing agent 0.01 to 2 pts.wt. defoaming agent, 0.01 to 3.0 pts.wt. thickener and, if necessary, 0.01 to 5 pts.wt. slaked lime having a grain size of ≤0.1mm as the powder additives. with 100 pts.wt. cement.